

Amendment Under 37 CFR 1.111
U.S. Application No. 10/009,822

AMENDMENTS TO THE SPECIFICATION

Please change table 1 at page 16 as follows:

Table 1

Type			A	B	C	D	E	F
Primary Thickness T_1 (mm)			3.1	3.7	3.4	5.5	8.0	12.0
Secondary Thickness T_2 (mm)			1.1	1.1	1.1	1.1	1.1	1.1
Secondary Rolling Rate (%)			65	70	75	80	86	91
Coefficient of Linear Expansion	Secondary Rolling Direction	(30 - 400 °C)	9.0	8.7	8.5	8.1	7.7	7.5
		(30 - 800 °C)	8.4	8.2	7.9	7.6	7.2	7.0

Coefficient of Linear Expansion: in $10^{-6}/K$

Note: Since the Examiner indicated that the amendments to the table could not be done by Examiner's Amendment, Applicants have presented the table in a form for publication. Applicants note that the changes required adding the °C mark to the table.